

BRITISH STANDARD**BS EN
12099 : 1997
BS 2782 :
Part 11 :
Method 1103E :
1997**

Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content

The European Standard EN 12099 : 1997 has the status of a
British Standard

ICS 23.040.20; 23.040.45;

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

MEHR AB HAYAT SANAAT KERMAN
www.MAHCOpipe.com



BS EN 12099 : 1997

National foreword

This British Standard is the English language version of EN 12099 : 1997 published by the European Committee for Standardization (CEN).

The UK participation in its preparation was entrusted to Technical Committee PRI/61, Plastics piping systems and components, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

This European Standard is also incorporated into BS 2782 *Methods of testing plastics : Part 11 Thermoplastics pipes, fitting and valves*, as Method 1103E : 1997, for association with related test methods for plastics materials and plastics piping systems.

It is also for use for the revision or amendment of other national standards as practicable, but it should not be presumed to apply to any existing standard or specification which contains or makes reference to a different test method until that standard/specification has been amended or revised to make reference to this method and any requirements adjusted as appropriate.

NOTE : Subclause 4.1 states that test pieces may be cut from a cross-section of a pipe or fitting. For a test method for determining the content of volatile material, it is essential that the cutting technique does not heat the test piece to an extent that would expel any material and thereby affect the results. In the absence of any related instructions by a referring standard, the responsible BSI committee considers that the cutting method should not induce any tangible heating or involve any coolant which could be adsorbed.

Warning note. This British Standard, which is identical with EN 12099 : 1997, does not necessarily detail all the precautions necessary to meet the requirements of the Health and Safety at Work etc. Act 1974. Attention should be paid to any appropriate safety precautions and the method should be operated only by trained personnel.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 4, an inside back cover and a back cover.

Amendments issued since publication

Amd. No.	Date	Text affected

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 December 1997

© BSI 1997

ISBN 0 580 28748 3

MEHR AB HAYAT SANAAT KERMAN
www.MAHCOpipes.com

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 12099

May 1997

ICS

Descriptors: Fluid pipelines, plastics tubes, polyethylene, chemical analysis, determination of content, volatile matter

English version

Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content

Systèmes de canalisations en plastiques —
Matériaux et composants de tuyauterie en
polyéthylène — Détermination de la teneur en
matières volatiles

Kunststoff-Rohrleitungssysteme —
Polyethylen-Rohrleitungswerkstoffe und — teile —
Bestimmung des Gehalts an flüchtigen
Bestandteilen

This European Standard was approved by CEN on 1997-03-28. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

MAHCO
CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

© 1997 CEN — All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 12099 : 1997 E

MEHR AB HAYAT SANAAAT KERMAN
www.MAHCOpipe.com

Foreword

This European standard has been prepared by Technical Committee CEN/TC 155, Plastics piping systems and ducting systems, the secretariat of which is held by NNL.

The material-dependent parameters and/or performance requirements are incorporated in the System Standard(s) concerned.

This standard is one of a series of standards on test methods which support System Standards for plastics piping systems and ducting systems.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1997, and conflicting national standards shall be withdrawn at the latest by November 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

The logo for MAHCO is a large, stylized, light blue graphic consisting of several overlapping, angular shapes that form a complex, abstract design. Below this graphic, the word "MAHCO" is written in a large, bold, light blue serif font.

MAHCO

1 Scope

This standard specifies a method for determining the content of material volatile at 105 °C in polyethylene (PE) piping materials.

This method is applicable to moulding and extrusion materials. It can also be applicable to components in PE piping systems.

2 Principle

The method consists of determining the loss of mass of a test piece which has been put in a drying oven at a given temperature.

NOTE. It is assumed that the following test parameters are set by the standard making reference to this standard:

- the source and form of the test piece (see 4.1);
- number of test pieces (see 4.2).

3 Apparatus

3.1 *Drying oven or equivalent device, capable of maintaining the temperature at (105 ± 2) °C at the position for the cup(s) (see 3.2 and 5.4).*

3.2 *A cylindrical glass weighing cup, with a diameter of 35 mm capable of containing a test piece (see 4.1), a minimum volume of 50 ml and a corresponding lid.*

3.3 *A desiccator.*

3.4 *An analytical balance or equivalent, capable of weighing to the nearest 0,1 mg.*

4 Test piece

4.1 Each test piece shall comprise an approximately 25 g portion of a sample representative of the material before moulding or extrusion, as applicable, or cut in accordance with the referring standard from a cross section of a pipe or fitting.

NOTE. If test samples utilize different sampling weights or are taken from different sources, e.g. raw material granulate or finished product, then there may be a difference in test results obtained. This may depend on e.g. the surface area/mass ratio or the maximum thickness of material. To demonstrate correlation with results for granulate samples determined in accordance with this standard, the preparation of samples from finished product may have to be modified.

4.2 The number of test pieces shall be as specified in the referring standard.

5 Procedure

5.1 Clean and dry a weighing cup and its lid (3.2) until constant weight is achieved and store them in the desiccator (3.3) for at least 0,5 h at room temperature.

5.2 Take the weighing cup and its lid out of the desiccator and determine their combined mass, m_0 , to the nearest 0,1 mg. Replace the lid in the desiccator.

5.3 Fill the cup with about 25 g portion of the sample and determine the mass, m_1 of the cup, lid and the test portion to the nearest 0,1 mg.

5.4 Put the weighing cup in the drying oven zone which is kept at (105 ± 2) °C (see 3.1).

5.5 After a period of (65 ± 5) min, take the weighing cup out of the drying oven and put the cup in the desiccator for at least 1 h at room temperature.

5.6 Cover the cup with the lid. Weigh the cup, lid and residual material to the nearest 0,1 mg, as mass m_2 .

6 Calculation

Calculate the volatile material content, m_v , of the test portion using the following equation:

$$m_v = \frac{m_1 - m_2}{m_1 - m_0} \times 10^6$$

where:

m_v is the volatile material content in milligrams per kilogram (mg/kg) at (105 ± 2) °C;

m_0 is the mass in grams of the empty weighing cup and its lid;

m_1 is the mass in grams of the weighing cup and its lid plus the test portion;

m_2 is the mass in grams of the weighing cup and its lid plus the residual material after 1 h at (105 ± 2) °C.

7 Test report

The test report shall include the following information:

- the reference to this standard and to the referring standard;
- the complete identification of the test piece;
- the source and form of the material;
- the test temperature;
- the number of test portions tested;
- the calculated volatile material content, in milligrams per kilogram (mg/kg) for each test portion;
- any factors which may have affected the results, such as any incidents or any operating details not specified in this standard;
- the date of the test.

BS EN 12099 :
1997
BS 2782 :
Part 11 :
Method 1103E :
1997

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Contract requirements

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the responsible technical committee, the identity of which can be found on the inside front cover. Tel: 0181 996 9000; Fax: 0181 996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services, Sales Department at Chiswick: Tel: 0181 996 7000; Fax: 0181 996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library, the Standardline Database, the BSI Information Technology Service (BITS) and its Technical Help to Exporters Service. Contact the Information Department at Chiswick: Tel: 0181 996 7111; Fax: 0181 996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Customer Services, Membership at Chiswick: Tel: 0181 996 7002; Fax: 0181 996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager, BSI, 389 Chiswick High Road, London W4 4AL.

BSI
389 Chiswick High Road
London
W4 4AL