INTERNATIONAL STANDARD

ISO 4440-2

> First edition 1994-10-01

Thermoplastics pipes and fittings — Determination of melt mass-flow rate —

Part 2:

Test conditions

Tubes et racords en matières thermoplastiques — Détermination de l'indice de fluidité à chaud en masse —

Partie 2: Paramètre d'essai



Reference number ISO 4440-2:1994(E)

MEHR AB HAYAT SANAAT KERMAN www.MAHCOpipe.com

ISO 4440-2:1994(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 4440-2 was prepared by Technical Committee ISO/TC 138, Plastics pipes, fittings and valves for the transport of fluids, Subcommittee SC 5, General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications.

This first edition of ISO 4440-2, together with ISO 4440-1:1994, cancels and replaces ISO 4440:1980, which has been technically revised.

ISO 4440 consists of the following parts, under the general title *Thermo-* plastics pipes and fittings — Determination of melt mass-flow rate:

- Part 1: Test method
- Part 2: Test conditions

Annex A of this part of ISO 4440 is for information only.

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

ii MEHR AB HAYAT SANAAT KERMAN www.MAHCOpipe.com

ISO 4440-2:1994(E)

Thermoplastics pipes and fittings — Determination of melt mass-flow rate —

Part 2:

Test conditions

1 Scope

This part of ISO 4440 specifies conditions for the determination of the melt mass-flow rate (MFR) of polyolefin materials from pipes or fittings. It is applicable to all polyolefin materials characterized by such measurements, as detailed in clause 3.

For the test method, see ISO 4440-1.

2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this part of ISO 4440. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this part of ISO 4440 are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 4440-1:1994, Thermoplastics pipes and fittings — Determination of melt mass-flow rate — Part 1: Test method.

3 Test conditions

The test conditions are given in table 1, for the materials detailed therein.



1

MEHR AB HAYAT SANAAT KERMAN www.MAHCOpipe.com

ISO 4440-2:1994(E) © ISO

Table 1 — Test parameters

Thermoplastic material	Condition	Test temperature θ °C	Nominal mass m _{nom} kg	Reference time t _{ref} S
Polyethylene (PE)	4 7 18	190 190 190	2,160 21,600 5,000	600 600
Polypropylene (PP)	12	230	2,160	600
	18	230	5,000	600
Polybutylene (PB)	4	190	2,160	600
	6	190	10,000	600
	18	190	5,000	600



MEHR AB HAYAT SANAAT KERMAN www.MAHCOpipe.com

Annex A

(informative)

Bibliography

[1] ISO 1133:1991, Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics.



MEHR AB HAYAT SANAAT KERMAN www.MAHCOpipe.com

IZO 4440 PT*2 94 **= 4851903 0576565 2T0 =**

ISO 4440-2:1994(E) © ISO



ICS 23.040.20; 23.040.45

Descriptors: pipes (tubes), pipe fittings, plastics products, thermoplastic resins, plastic tubes, tests, determination, melting, testing conditions.

Price based on 3 pages

MEHR AB HAYAT SANAAT KERMAN www.MAHCOpipe.com

COPYRIGHT 2000 International Organization For Standardization Information Handling Services, 2000